



QUALITY CERTIFICATE CTB WPC DECKING CERTIFICATION

WPC (Wood Polymer Composite) profiles intended for the production of decking on spaced supports.

Non bearing product (pedestrian use only*)

*Are suitable for people traffic. Are not suitable to receive localized concentrated loads applied for long term, except if applied right above the discontinuous substructure (beams, joists, mechanically dimensioned accordingly).

Company : CPG BUILDING PRODUCTS
Product : RELIABOARD
Identification N°: 06-01

The product mentioned here is certified by FCBA. It is entitled to the right of use of the Collective Certification Mark CTB WPC Decking under the conditions requested in the General Rules and the Regulations of the Mark. In case of dispute, only the French version of this certificate is the authentic text

PROPERTIES

▶ Mechanical properties :

- *Bending:*
 - Normal conditions (20°C, 65% HR)
 - Limit temperatures conditions (-18°C / + 60°C)
 - After physical ageing
- *Creep resistance at high temperature :*

- *Hardness*

▶ Physical properties :

- *Behavior in terms of dimensional stability in limit temperature and humidity conditions*
- *Slip resistance*

▶ Characteristics of durability against biological agents

▶ Appearance durability

▶ Relevancy of the information given on the technical documents

▶ Note :

- Only flat grain side on top

CHARACTERISTICS

Modulus of elasticity at 20°C: $E_m = 2496$ MPa
at 60°C: $E_m = 1342$ MPa

Flexural resistance at 20°C : $f_m = 15.7$ MPa
at 60°C : $f_m = 8.8$ MPa

(characteristic value at 5% exclusion)

Creep coefficient : $C_f = 3.96$

Rate of creep recovery : $CR = 0.43$

Elastic recovery : $RE = 20.87$

Brinell hardness : $HB = 60$ MPa

Recovery rate : $Re = 86.4\%$

Thermal expansion coefficient :
 $\delta = 29.9 \cdot 10^{-6}$ ($^{\circ}C^{-1}$) (Lengthwise)

SRT Indice: Flat grain side

Longitudinal : dry : 58.1 / wet : 44.1

Transversal : dry : 74.0 / wet : 51.3

Resistance to wood destroying fungi
(resistant to water uptake)

Stable system according to EN 927-2

(Informative values : chalking : 4 / general aspect : 5)



ACCREDITATION
N° 5-0011
PORTEE
DISPONIBLE SUR
WWW.COFRAC.FR

NOTE:

This certificate applies only to products labelled with the logo of the mark.

This certificate attests the quality of productions, based on continuous monitoring. It can not prejudge the decisions that could be taken during the year, after examination of the results of this control. The updated lists of the holders of the mark and the list of the certified products are available at FCBA and at www.fcba.fr website.

FCBA, Certification body

10, rue Galilée
77420 Champs sur Marne
Tél : +33 (0)1 72 84 97 84

www.fcba.fr



INSTITUT TECHNOLOGIQUE

For the certification body

Certificate N° 516-16-2061-GB
Cancel and replace n°516-16-2003-GB

Date : 28/01/2016
Valid until 31/12/2016

LE DIRECTEUR CERTIFICATION
Alain HOCQUET